

CHANGES TO THE SPECIFICATION

Please substitute the following marked up paragraph(s) for the paragraph(s) now appearing in the currently filed specification:

Page 8, lines 3-7

Given that it is needed to favor recrystallization of the alloy as much as possible, it is necessary to limit the content of anti-recrystallizing elements, such as chromium, vanadium, hafnium and scandium, by keeping their maximum content below 0.01%, for example.
